# AP/Armaflex® AP/Armaflex® FS

Sheet & Roll Insulation

The original, fiber-free, flexible elastomeric pipe, valve and duct insulation for reliable protection against condensation, mold and energy loss.

AP Armaflex FS is PVC free.



- Fiber-free, formaldehyde-free, low VOC and non-particulating formulation protects indoor air quality
- Closed-cell structure provides excellent condensation control
- Built-in vapor barrier eliminates need for additional vapor retarder
- Microban® antimicrobial product protection inhibits the growth of mold and mildew in the insulation
- 25/50 rated for use in air plenums up to 1" thickness in AP Armaflex and 1-1/2" and 2" thickness in AP Armaflex FS
- Thickness up to 2" with R-value up to R-8









# Technical Data: AP Armaflex® and AP Armaflex® FS Sheet and Roll Insulation

### **Description:**

Black flexible closed-cell elastomeric thermal insulation in sheet and roll form

### Specifications Compliance:

ASTM C 534, Type II -Sheet Grade 1 ASTM C 1534 ASTM D 1056, 2B1

ASTM E 84, NFPA 255, UL723 ASTM G21/C1338 ASTM G22 CAN/ULC S102 ①

MEA 107-89M MIL-P-15280J, FORM S © MIL-C-3133C (MIL STD 670B) Grade SBE 3 © NFPA 90A, 90B UL 181

UL 94 5V-A, V-0, File E55798 City of LA - RR 7642

## Approvals, Certifications, Compliances:

- GREENGUARD Gold Certified.
- Manufactured without CFCs, HFCs, HCFCs, PBDEs, or Formaldehyde.
- Made with EPA registered Microban® antimicrobial product protection.
- All Armacell facilities in North America are ISO 9001:2008 certified.

Specifications:	Values	Test Method:		
	AP Armaflex Through 1"	AP Armaflex FS 1-1/2" & 2"	AP Armaflex 1-1/2" & 2"	
Thermal Conductivity: Btu • in./h •	ft² • °F (W/mK)			
75°F Mean Temperature (24°C) 90°F Mean Temperature (32°C)	0.245 (0.0353) 0.254 (0.0366)	0.28 (0.040) 0.286 (0.041)	0.25 (0.036) 0.256 (0.037)	ASTM C 177 or C 518
<b>Water Vapor Permeability:</b> Perm-in. [Kg/(s • m • Pa)]	0.05 (0.725 x 10 <sup>-13</sup> )	0.08 (1.16 x 10 <sup>-13</sup> )	0.05 (0.725 x 10 <sup>-13</sup> )	ASTM E 96, Procedure A
Flame Spread and Smoke Developed Index:	25/50 rated	25/50 rated	Does not pass	ASTM E 84 CAN/ULC S102 <sup>①</sup>
Water Absorption, % by Volume:	0.2%	0.2%	0.2%	ASTM C 209
Mold Growth: Fungi Resistance: Bacterial Resistance:	Passed	Passed	Passed	UL181 ASTM G21/C1338 ASTM G22
Upper Use Limit:	220°F (105°C) 3	300°F (149°C) 4	220°F (105°C) 3	ASTM C534
Lower Use Limit: <sup>⑤</sup>	-297°F (-183°C) ®	-297°F (-183°C) <sup>©</sup>	-297°F (-183°C) <sup>©</sup>	ASTM C534
Ozone Resistance:	GOOD	GOOD	GOOD	Ozone Chamber Test

R-Value:	R-1.6	R-2.1	R-3.1	R-4.2	R-6	R-8
Thickness:	3/8"	1/2"	3/4"	1"	1-1/2"	2"

Sizes:				
Sheet: Width x Length Thickness (nominal)	36" x 48" (.915m x1.22m) 1/8", 1/4", 3/8", 1/2", 3/4", 1", 1-1/2" & 2" (3, 6,10, 13, 19, 25, 38 & 50mm)			
Roll: Width Thickness (nominal) x Length	48" wide (1.22m) 3/8" x 100' (10mm x 30.5m) 1" x 35' (25mm x 10.7m) 1/2" x 70' (13mm x 21.4m) 3/4" x 50' (19mm x 15.2m) 1" x 35' (25mm x 10.7m) 1-1/2" x 25' (38mm x 7.6m) 2" x 18' (50mm x 5.4m)			
Outdoor Use	Painting with WB Finish or other protective jacketing is required to prevent damage to the insulation in exterior applications and to comply with the insulation protection sections of the International Energy Conservation Code (IECC) and ASHRAE 90.1.			

- ① AP Armaflex meets CAN/ULC S102 through 1" thickness.
- ② AP Armaflex meets MIL-P-15280J, FORM S and MIL-C-3133C (MIL STD 670B) Grade SBE through 1" thickness.
- 3 AP Armaflex and AP Armaflex FS Sheet and Roll Insulation withstand temperature of 250°F (121°C) when tested according to ASTM C 411. "Test Method for Surface Performance of High-Temperature Insulations." At this temperature, AP Armaflex Sheet and Roll Insulation shows no evidence of flaming, glowing, smoldering, delamination, melting or insulation collapse. Although this insulation will withstand high temperatures, continuous use temperature should be limited to 220°F (105°C).
- ④ AP Armaflex FS is formulated with EPDM rubber giving it a higher upper use temperature than AP Armaflex.
- (5) At temperatures below -20°F (-29°C), elastomeric insulation starts to become less flexible. However, this characteristic does not affect thermal efficiency and resistance to water vapor permeability of Armaflex insulation.
- © For applications of -40°F to -297°F (-40°C to -183°C), contact Armacell.

**ARMACELL LLC** TEL: 800.866.5638

FAX: 919.304.3847

info.us@armacell.com www.armacell.us 7600 Oakwood Street Extension, Mebane, NC 27302



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice. \* Microban product protection is limited to the product itself and is not designed to protect the users of these products from disease causing microorganisms, or as a substitute for normal cleaning and hygiene practices. Microban International, Ltd. makes neither direct nor implied health claims for the products containing Microban® antimicrobial product protection. Data, photomicrographs and information presented are based on standard laboratory tests and are provided for comparative purposes to substantiate antimicrobial activity for non-public health uses. Microban is a registered trademark of Microban International, Ltd.

AP Armaflex & FS	Sheet Roll	Submittal	015	Eng/USA	5/2016	l
------------------	------------	-----------	-----	---------	--------	---